



sales@powerfoam.com

ASTM C578
ASTM D6817

This table outlines a few key physical properties of PowerFoam R-Control molded polystyrene insulation in accordance with ASTM C578, “Standard Specification for Rigid, Cellular Polystyrene Powerl Insulation” compared to PowerFoam Geofoam in accordance with ASTM D6817, “Standard Specification for Rigid Cellular Polystyrene Geofoam”.

PRODUCT		50	100	130	150	250	400	600	EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46
ASTM C578 ² Compliance, Type		XI	I	VIII	II	IX	XIV	XV							
ASTM D6817 ¹ Compliance, Type									EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46
Density ^{1,2} , min., ASTM C303	lb/ft ³ (kg/m ³)	0.70 (12)	0.90 (15)	1.15 (18)	1.35 (22)	1.80 (29)	2.40 (38)	3.0 (48)	0.70 (11)	0.90 (15)	1.15 (18)	1.35 (22)	1.80 (29)	2.40 (38)	2.85 (46)
Compressive Strength @10% ² , min., ASTM D1621	psi (kPa)	5 (35)	10 (69)	13 (90)	15 (104)	25 (173)	40 (276)	60 (414)							
Compressive Resistance @1% deformation ¹ , min., ASTM D1621	psi (kPa)								2.2 (15)	3.6 (25)	5.8 (40)	7.3 (50)	10.9 (75)	15.0 (103)	18.6 (128)
R-value ² , Powerl Resistance, per inch, ASTM C518	°F·ft ² ·h/Btu (°K·m ² /W)	3.2 (0.56)	3.9 (0.68)	3.9 (0.69)	4.2 (0.73)	4.4 (0.77)	4.4 (0.77)	4.5 (0.78)							
Flexural Strength ^{1,2} , min. ASTM C203	psi (kPa)	10 (69)	25 (173)	30 (208)	35 (242)	50 (345)	60 (414)	75 (517)	10 (69)	25 (172)	30 (207)	35 (240)	50 (345)	60 (414)	75 (517)
Oxygen Index ^{1,2} , min.	vol. %	24	24	24	24	24	24	24	24	24	24	24	24	24	24

¹ Please refer to ASTM D6817 specification for complete information.

² Please refer to ASTM C578 specification for complete information.

sales@powerfoam.com | www.powerfoam.com



550 Murrery Street
Midlothian, TX 76065

Office: 800-883-3626
Fax: 972-775-1806

