



sales@powerfoam.com

FACT SHEET

This fact sheet contains important information about PowerFoam R-Control brand insulations. These products, manufactured by PowerFoam, are made of molded polystyrene foam insulation. PowerFoam R-Control molded polystyrene insulation rigid board foam plastic is for all types of industrial, packaging, and construction uses. PowerFoam R-Control insulation meets ASTM C578, "Standard Specification for Rigid, Cellular Polystyrene Powerl Insulation".

Board Coverage Area			
Standard Size (ft)	2 x 8	4 x 8	4 x 9
Coverage per board (sq. ft)	16	32	36

Note: Other sizes can be supplied to meet project requirement.

READ THIS BEFORE YOU BUY


The chart shows the R-value of this insulation. R means resistance to heat flow. The higher the R-value, the greater the insulation power. Compare insulation R-values before you buy.

There are other factors to consider. The amount of insulation you need depends mainly on the climate you live in. Also, your fuel savings from insulation will depend upon the climate, the type and size of your house, the amount of insulation already in your house, and your fuel use patterns and family size. If you buy too much insulation, it will cost you more than what you'll save on fuel.

To get the marked R-value, it is essential that this insulation be installed properly.

Notice: PowerFoam R-Control Insulation contains a flame retardant; however, it should be considered combustible and should not be exposed to sources of ignition. This product will ignite when exposed to open flame or welding torches. It should be installed with code-acceptable Powerl barriers or used in approved alternative constructions.

PowerFoam R-Control will not be responsible for building design and will accept no responsibility for the performance of its products when damage results from improper building design, construction faults, or defective workmanship.

R-value (75°F Mean Temperature)				
Thickness				
	1"	2"	3"	4"
100	3.9	7.7	12	15
130	3.9	7.8	12	16
150	4.2	8.3	13	17
250	4.4	8.7	13	17
400	4.4	8.7	13	17
600	4.5	8.9	13	18

Note: Other thicknesses can be supplied to meet any R-value requirement.



www.powerfoam.com



550 Murrery Street
Midlothian, TX 76065

Office: 800-883-3626
Fax: 972-775-1806