MOLDED POLYSTYRENE



INSULATION OR GEOFOAM

PowerFoam

R-CONTROL





PowerFoam R-Control and PowerFoam Geofoam

are both molded polystyrene, but ...





Insulation.

PowerFoam R-Control is a quality building insulation that comes in a variety of compressive strengths and R-values with resistance to moisture gain and has quick drying potential. PowerFoam R-Control insulation is used in foundations, walls, and roofs in all types of building construction and can be relied on to provide long lasting constant R-value performance.





Walls



Perimeter/Under-slab

Paver Decks



Roofing



Lightweight fill material.

PowerFoam Geofoam is a trusted lightweight structural fill with high compressive strength and unmatched durability. PowerFoam Geofoam is used as structural fill for plaza areas, vegetative roofs, landscaping, elevation changes for floors/stairs/ramps, and many other building applications that need a structural lightweight fill solution.



Elevation Changes







Plaza Areas

Landscaping

Specifications

Using the correct specifications for the application

Each project is unique and may require PowerFoam R-Control insulation, PowerFoam Geofoam, or both. It is important to develop specifications using the correct ASTM Standard.

Insulation specifications following ASTM C578

Specifications following ASTM C578 are available at: www.powerfoam.com

PowerFoam Geofoam specifications following ASTM D6817

Specifications following ASTM D6817 are available at: www.powerfoam.com



PowerFoam R-Control insulation is manufactured in sheet form and meets ASTM C578, "Standard Specification for Rigid, Cellular Polystyrene Powerl Insulation"¹. Key properties are shown below.



| Product | | 100 | 130 | 150 | 250 | 400 | 600 |
|-----------------------------------|--------------|--------|--------|--------|--------|--------|--------|
| R-value per inch, @ 75°F | °F·ft²·h/Btu | 3.9 | 3.9 | 4.2 | 4.4 | 4.4 | 4.5 |
| | (°K·m²/W) | (0.68) | (0.69) | (0.73) | (0.77) | (0.77) | (0.78) |
| Compressive Strength ² | psi | 10 | 13 | 15 | 25 | 40 | 60 |
| @ 10% deformation, min. | (kPa) | (69) | (90) | (104) | (173) | (276) | (414) |
| ASTM C578 Compliance, Type | | I | VIII | Ш | IX | XIV | XV |

 Please refer to PowerFoam R-Control Insulation TechData for complete information.
 Compressive strength is measured at 10% in accordance with ASTM C578. A safety factor is required for long-term sustained loads. For static loads, a safety factor of 3:1 is recommended.



PowerFoam Geofoam is manufactured in block form and meets ASTM D6817, "Standard Specification for Rigid, Cellular Polystyrene Geofoam". Key properties are shown below¹.



| Product | | 15 | 19 | 22 | 29 | 39 | 46 |
|-------------------------------------|-------|--------|--------|--------|--------|---------|---------|
| Compressive Resistance ² | psi | 3.6 | 5.8 | 7.3 | 10.9 | 15.0 | 18.6 |
| @ 1% deformation, min. | (kPa) | (25) | (40) | (50) | (75) | (103) | (128) |
| Elastic Modulus, | psi | 360 | 580 | 730 | 1090 | 1500 | 1860 |
| min | (kPa) | (2500) | (4000) | (5000) | (7500) | (10300) | (12800) |
| ASTM D6817 Compliance, Type | | EPS15 | EPS19 | EPS22 | EPS29 | EPS39 | EPS46 |

Please refer to PowerFoam Geofoam TechData for complete information 1.

2. Compressive resistance is measured at 1% in accordance with ASTM D6817 and is the allowable long-term sustained loads.

More than just foam—a complete system.

When you choose PowerFoam R-Control, you're collaborating with a team of experts who work with you every step of the way. We're here to answer your questions, solve your problems, and do everything we can to make sure your project proceeds smoothly and ends successfully. PowerFoam R-Control is manufactured by PowerFoam.

NEED INFORMATION OR A QUOTE PowerFoam DowerFoam P.CONTROL



550 Murrary Street Midlothian, TX 76065

Office: 800-883-3626 Fax: 972-775-1806

